Laxmi Polyadditives. India

Product Data Sheet

Grade: CZ-4008



Product Description:

It is a Heterogeneous mixture of metallic Stearates, non toxic organic stabilizers, waxes, and antioxidants produced by simple blending. It avoids weighing and mixing of individual stabilizers which reduces the weighing error and too much inventory of various stabilizers & lubricants. One bag type production, easy and convenient It has a good balance of internal and external lubrication,

Technical Specification:

PARAMETERS SPECIFICATIONS

Appearance : Off White Powder

Bulk Density : 400-550 g/l
Dropping Point : 90-110°C
Free fatty Acid : 0.5 % max
Volatile Matter : 0.5% max

Ca/Zn One Pack is homogeneous mixture—using high quality Stearic acid and exhibits the following properties:-Excellent lubricity, Excellent water repellant, Good clarity and weathering stabilizer, Non toxicity, Non sulfide staining, Little initial color formation

SOLUBILITY

Ca/Zn One Pack is insoluble in water and alcohol, ether; but soluble in benzene, acids or common solvents when hot

SUGGESTED APPLICATIONS: PVC Cable ,Automotive cable / White goods / House Wire, PVC co- compounding .

STORAGE

Ca/Zn One Pack has long storage life if kept cool and dry.

Indoor storage is recommended, Store in cool, dry, ventilated place.

Keep away from heat and sources of ignition. Do not breathe dust. Avoid contact with eyes.

PACKING

Ca/Zn One Pack is available in 25 kgs HDPE Bag

SAFETY & ENVIRONMENTAL INFORMATION

Avoid contact with skin, eyes and clothing: may cause irritation. Wear protective safety glasses. Use personal protective equipment. Ensure adequate ventilation. Avoid dust formation. Remove all sources of ignition. Do not breathe vapors/dust. do not allow material to contaminate ground water system. Do not let product enter drains.

Office:

Laxmi Polyadditives 902 GIDC, Sarigam

Dist: Valsad -396155, Gujarat

Email: drpw66@hotmail.com, mobile: 9712381788,0260-2780074.

The technical information and suggestion for use contained herein are believed to be reliable, but they are not to be constructed as warranties and no patent liability can be assumed.