Laxmi Polyadditives. India

Product Data Sheet



CALCIUMSTEARATE - PREMIUM

PARAMETERS SPECIFICATIONS

 Metal (%)
 : 6.5 - 7.5

 Loss on drying (%)
 : 3 Max

 FFA (%)
 : 1 Max

 Bulk Density
 : 250-310

 Melting Point (₀C)
 : 140-160

Particle Size : Min. 99% through 240 mesh screen

Physical Form : Fine Powder

DESCRIPTION

CALCIUMSTEARATE PREMIUM is made via the modified fusion process using high quality Stearic acid and exhibits the following properties: Stabilizing, Excellent lubricity, Water repellant, gelling,

SOLUBILITY

CALCIUMSTEARATE PREMIUM is insoluble in water and alcohol, ether; but soluble in benzene, acids or common solvents when hot.

SUGGESTED APPLICATIONS

Plastics : as a chloride ion catcher in pe, pp polymerization.

Rubber : as mould release agent.

Cosmetics : as additive to promote smoothing effect.

Building material, fabric : as water proofing agent.

Fuel : as additive to reduce exhaust gas pollution.

Grease : as thickener.

Paints : as flatting agent and coating agent.

Wire drawing : as lubricant.

Fertilizers and explosives : as hydrophobic agent.

Food industry : as conditioning agent, and antifoaming agent.

Foundry ; insectides, Pesticides : as additive

Pharmaceuticals : as lubricant in making tablets.

Pencil and crayons : as lubricant.

<u>STORAGE</u> <u>PACKING</u>

if kept cool and dry.

Indoor storage is recommended, Store in cool, dry,

ventilated place.

Keep away from heat and sources of ignition. Do not

breathe dust. Avoid contact with eyes.

SAFETY & ENVIRONMENTAL INFORMATION

Avoid contact with skin, eyes and clothing: may cause irritation. Wear protective safety glasses. Use personal protective equipment. Ensure adequate ventilation. Avoid dust formation. Remove all sources of ignition. Do not breathe vapors/dust. do not allow material to contaminate ground water system. Do not let product enter drains.

25 kgs HDPE Bag

Office:

Laxmi Polyadditives 902 GIDC, Sarigam

Dist: Valsad -396155, Gujarat

Email: <u>drpw66@hotmail.com</u>, <u>mobile</u>: 9712381788,0260-2780074.

The technical information and suggestion for use contained herein are believed to be reliable, but they are not to be constructed as warranties and no patent liability can be assumed.