Laxmi Polyadditives. India

Product Data Sheet



ZINC STEARATE - INDUSTRIAL

PARAMETERS SPECIFICATIONS

 Metal (%)
 : 6.8 - 8

 Metal Oxide(Ash) (%)
 : 17.0- 18.0

 Loss on drying (%)
 : 0.5 Max

 FFA (%)
 : 1 Max

 Bulk Density (g/l)
 : 230 - 500

 Melting Point (oC)
 : 120-128

Partical Size : Min. 99% through 240 mesh screen

Physical Form : Fine Powder

.

ZINC STEARATE INDUSTRIAL is made via the modified fusion process using high quality Stearic acid and exhibits the following properties: Excellent lubricity, Excellent water repellant, Good clarity and weathering stabilizer, Non toxicity, Non sulfide staining, Little initial colour formation

SOLUBILITY

ZINC STEARATE INDUSTRIAL is insoluble in water and alcohol, ether; but soluble in benzene, acids or common solvents when hot.

SUGGESTED APPLICATIONS

Plastics : As external lubricant & stabilizer for PP,PE,ABS and Co-stabilizer for Rubber

: As mould release agent. Also used as dusting agent.

Paints , pigments : As dispersing agent. Also used as flatting agent and

and varnishes sanding agent in lacquers.

Building material, : As water proofing agent. Textiles and paper

STORAGE PACKING

ZINC STAERATE INDUSTRIAL has long storage life if

kept cool and dry.

Indoor storage is recommended, Store in cool, dry,

ventilated place.

Keep away from heat and sources of ignition. Do not

breathe dust. Avoid contact with eyes.

ACKING

ZINC STARATE INDUSTRIAL is available in

25 kgs HDPE Bag

SAFETY & ENVIRONMENTAL INFORMATION

Avoid contact with skin, eyes and clothing: may cause irritation. Wear protective safety glasses. Use personal protective equipment. Ensure adequate ventilation. Avoid dust formation. Remove all sources of ignition. Do not breathe vapors/dust. do not allow material to contaminate ground water system. Do not let product enter drains.

Office:

Laxmi Polyadditives 902 GIDC, Sarigam

Dist: Valsad -396155, Gujarat

Email: drpw66@hotmail.com, mobile: 9712381788,0260-2780074.

The technical information and suggestion for use contained herein are believed to be reliable, but they are not to be constructed as warranties and no patent liability can be assumed.