Laxmi Polyadditives. Jndia

Product Data Sheet



ZINC STEARATE – PREMIUM

| PARAMETERS | SPECIFICATIONS |
|----------------------|------------------------------------|
| Metal (%) | : 10-11.2 |
| Metal Oxide(Ash) (%) | : 12.5-14.0 |
| Loss on drying (%) | : 0.5 Max |
| FFA (%) | : 1 Max |
| Bulk Density (g/l) | : 230 - 350 |
| Melting Point (oC) | : 120-128 |
| Partical Size | : Min. 99% through 240 mesh screen |
| Physical Form | : Fine Powder |

ZINC STEARATE PREMIUM is made via the modified fusion process using high quality Stearic acid and exhibits the following properties :- Excellent lubricity, Excellent water repellant, Good clarity and weathering stabilizer , Non toxicity, Non sulfide staining , Little initial colour formation

SOLUBILITY

ZINC STEARATE PREMIUM is insoluble in water and alcohol, ether; but soluble in benzene, acids or common solvents when hot.

SUGGESTED APPLICATIONS

Plastics: As external lubricant & stabilizer for PP,PE,ABS and Co-stabilizer for Rubber
: As mould release agent. Also used as dusting agent.Paints , pigments: As dispersing agent. Also used as flatting agent and
and varnishes sanding agent in lacquers.Building material,: As water proofing agent. Textiles and paper

STORAGE

ZINC STAERATE PREMIUM has long storage life if kept cool and dry.

Indoor storage is recommended, Store in cool, dry, ventilated place.

Keep away from heat and sources of ignition. Do not breathe dust. Avoid contact with eyes.

SAFETY & ENVIRONMENTAL INFORMATION

Avoid contact with skin, eyes and clothing: may cause irritation. Wear protective safety glasses. Use personal protective equipment. Ensure adequate ventilation. Avoid dust formation. Remove all sources of ignition. Do not breathe vapors/dust. do not allow material to contaminate ground water system. Do not let product enter drains.

Office : Laxmi Polyadditives 902 GIDC, Sarigam Dist : Valsad -396155,Gujarat Email : <u>drpw66@hotmail.com , mobile</u> : 9712381788,0260-2780074.

The technical information and suggestion for use contained herein are believed to be reliable, but they are not to be constructed as warranties and no patent liability can be assumed.

PACKING

ZINC STARATE PREMIUM is available in 25 kgs HDPE Bag